



# THOR Tarp

DIV. OF **ODIN** INTERNATIONAL, INC



## WeldShield Fiberglass Sewing Thread Specifications

CONSTRUCTION & TWIST			
Size	Yarn	U. S. System	International
E-12	BC-4	ECBC 150 2/2 9.6Z	EC 4.0 33 2x2 372Z
E-18	BC-6	ECBC 150 2/3 9.1Z	EC 4.0 33 2x3 358Z
E-24	BC-8	ECBC 150 2/4 8.3Z	EC 4.0 33 2x4 327Z

SIZE / YIELD / STRENGTH							
Size	Diameter		Approximate Yield (Uncoated)		Approximate Yield (Coated)		% PTFE
	Inches	mm	Yds / Lb.	M / Kg.	Yds / Lb.	M / Kg.	
E-12	.014	.356	3,500	7,055	2,975	6,000	14.5-17%
E-18	.017	.432	2,330	5,000	2,000	4,030	14.5-17%
E-24	.020	.508	1,750	3,530	1,475	2,975	14.5-17%

Size	Tenacity	Minimum Break Strength		Average Break Strength		Average Knot Strength		Denier
		Lbs.	Kg.	Lbs.	Kg.	Lbs.	Kg.	
E-12	4.97 gm/den	12	5.44	18	8.17	5.8	2,63	1275
E-18	4.49 gm/den	18	8.16	24	10.89	6.3	2,86	1915
E-24*	4.79 gm/den	25	11.34	30	13.60	8.8	3,99	2550

\*Meets MIL-C 20079 H – Type III, Class 3 & ASTM D 4030-89

**Packaging:** Standard package is approximate 2 Lb. (.907 Kg.) Spool – 8 spools per carton

**FOB:** Cavetown, MD

**Terms:** Net 30 days (upon credit approval)

**Pricing:** Subject to change without notice

To the best of our knowledge, the information contained herein is accurate. The information provided is based upon data furnished by our suppliers. However, ODIN International, Inc. assumes no liability whatsoever for the accuracy or completeness of the information contained herein. While believed to be reliable, the information of products are intended for use by skilled persons at their own risk. Final determination of suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that those are the only hazards that exist.

CORPORATE HQ: P.O. Box 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511  
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM